



MAXREST PASSIVE[®]

OXIDE CONVERTER AND ANTI-CORROSIVE PROTECTION FOR REINFORCING RODS AND ALL OTHER IRON OR STEEL SURFACES

DESCRIPTION

MAXREST PASSIVE is a single component liquid material, ready to use as protection for reinforcing rods and other steel and iron surfaces against oxidation, acid and alkali attack. MAXREST PASSIVE will form part of the oxide as a passive layer giving full protection against corrosion, acid and alkali attack.

USES

- Oxide converter of corroded metal surfaces.
- As anti-corrosive protection for reinforcing steel in the restoration of structural concrete.
- As protection against attack from strong chemical agents.

APPLICATION INSTRUCTIONS

Surface preparation

Prior to application clean down affected area using a wirebrush, or by sandblasting or high water pressure and wash with water,. Remove dust with a damp cloth if necessary.

Application

MAXREST PASSIVE does not require dilution or addition of other materials. Apply by brush, spray gun or by immersing the article to be protected. Avoid staining the concrete around the reinforcement.

Product requirements

Recommended application 8 m²/liter and coat for a thickness of 50 micron DFT. For better assurance apply two coats.

Curing

Depending on temperature 2 to 3 hours before the application of final coatings. e. g. paints, polyurethane, epoxy or other DRIZORO Products.

CAUTION

Do not apply at temperatures below 5 °C or above 60 °C. Tools must be cleaned with water immediately after completion of application.

TECHNICAL DATA

Solid contents (%)	40
Density (kg / lt):	1.18 ± 0,02.
Product requirement	8 m ² /liter for 50 micron dry film thickness 150 grm/m ²
Fireproofing	Meets British Standard BS473 Part 7-1971

PACKAGING

1 liter and 5 and 25 liter jerrycans.

STORAGE

12 months in its original unopened container, in a dry covered place, protected from frost.

COLOUR

Milky white.

GUARANTEE

The information contained in this leaflet is based on our experience and technical knowledge, obtained through laboratory testing and from bibliographic material. DRIZORO reserves the right to introduce changes without prior notice. Any use of this data beyond the purposes expressly specified in the leaflet will not be the Company's responsibility unless authorised by us. We shall not accept responsibility exceeding the value of the purchased product.



DRIZORO, S.A.

C/ Primavera 50-52 Parque Industrial Las Monjas
28850 TORREJON DE ARDOZ – MADRID (SPAIN)
Tel. 91 676 66 76 - 91 677 61 75 Fax. 91 675 78 13

e-mail: info@drizoro.com Web site: drizoro.com

